

1310 nm band PANDA

Feature

- 1310 nm band polarization maintaining fiber

Common specifications

Concentricity error	≤ 0.5 μm
Cladding diameter	125 ± 1 μm (Major diameter)
Polarization crosstalk	≤ -30 dB/100m @ 1310 nm
Minimum bending radius	1% proof : R30 mm* 2% proof : R20 mm

Product list

Product	Mode field diameter	Attenuation	Cutoff wavelength	Beat length	Coating structure	Coating diameter
SM13-PS-H90D	9.0 ± 0.5 μm @ 1310 nm	≤ 1.0 dB/km @ 1310 nm	1130 - 1270 nm	2.5 - 4.0 mm @ 1310 nm	UV curable acrylate /Polyester elastomer (Color : Black)	900 ± 100 μm
SM13-PS-U40D					UV curable acrylate	400 ± 15 μm
SM13-PS-U25D						245 ± 15 μm
HA13-PS-U25D	5.5 ± 1.0 μm @ 1310 nm	≤ 2.0 dB/km @ 1310 nm	1000 - 1290 nm	≤ 2.5 mm @ 1310 nm		

*1% proof test type is standard. 2% proof test type is available, and code '-H' is added at the end of the product name. (e.g. SM15-PS-U40D-H)



Optical Fiber Division
1440, Mutsuzaki, Sakura, Chiba 285-8550, Japan

<http://www.fujikura.co.jp/>
optodevice@jp.fujikura.com

Specifications are subject to change without prior notice